



Thermal and Environmental Barrier Coatings for Advanced Turbine Engine Applications

Dongming Zhu

U.S. Army Research Laboratory, Glenn Research Center, Cleveland, Ohio

Robert A. Miller

Glenn Research Center, Cleveland, Ohio

The NASA STI Program Office . . . in Profile

Since its founding, NASA has been dedicated to the advancement of aeronautics and space science. The NASA Scientific and Technical Information (STI) Program Office plays a key part in helping NASA maintain this important role.

The NASA STI Program Office is operated by Langley Research Center, the Lead Center for NASA's scientific and technical information. The NASA STI Program Office provides access to the NASA STI Database, the largest collection of aeronautical and space science STI in the world. The Program Office is also NASA's institutional mechanism for disseminating the results of its research and development activities. These results are published by NASA in the NASA STI Report Series, which includes the following report types:

- **TECHNICAL PUBLICATION.** Reports of completed research or a major significant phase of research that present the results of NASA programs and include extensive data or theoretical analysis. Includes compilations of significant scientific and technical data and information deemed to be of continuing reference value. NASA's counterpart of peer-reviewed formal professional papers but has less stringent limitations on manuscript length and extent of graphic presentations.
- **TECHNICAL MEMORANDUM.** Scientific and technical findings that are preliminary or of specialized interest, e.g., quick release reports, working papers, and bibliographies that contain minimal annotation. Does not contain extensive analysis.
- **CONTRACTOR REPORT.** Scientific and technical findings by NASA-sponsored contractors and grantees.

- **CONFERENCE PUBLICATION.** Collected papers from scientific and technical conferences, symposia, seminars, or other meetings sponsored or cosponsored by NASA.
- **SPECIAL PUBLICATION.** Scientific, technical, or historical information from NASA programs, projects, and missions, often concerned with subjects having substantial public interest.
- **TECHNICAL TRANSLATION.** English-language translations of foreign scientific and technical material pertinent to NASA's mission.

Specialized services that complement the STI Program Office's diverse offerings include creating custom thesauri, building customized databases, organizing and publishing research results . . . even providing videos.

For more information about the NASA STI Program Office, see the following:

- Access the NASA STI Program Home Page at <http://www.sti.nasa.gov>
- E-mail your question via the Internet to help@sti.nasa.gov
- Fax your question to the NASA Access Help Desk at 301-621-0134
- Telephone the NASA Access Help Desk at 301-621-0390
- Write to:
NASA Access Help Desk
NASA Center for Aerospace Information
7121 Standard Drive
Hanover, MD 21076



Thermal and Environmental Barrier Coatings for Advanced Turbine Engine Applications

Dongming Zhu

U.S. Army Research Laboratory, Glenn Research Center, Cleveland, Ohio

Robert A. Miller

Glenn Research Center, Cleveland, Ohio

Prepared for the
2004 Fall Meeting
sponsored by the Materials Research Society
Boston, Massachusetts, November 29–December 03, 2004

National Aeronautics and
Space Administration

Glenn Research Center

Available from

NASA Center for Aerospace Information
7121 Standard Drive
Hanover, MD 21076

National Technical Information Service
5285 Port Royal Road
Springfield, VA 22100

Available electronically at <http://gltrs.grc.nasa.gov>

Thermal and Environmental Barrier Coatings for Advanced Turbine Engine Applications


Dongming Zhu
U.S. Army Research Laboratory
Glenn Research Center
Cleveland, Ohio 44135

Robert A. Miller
National Aeronautics and Space Administration
Glenn Research Center
Cleveland, Ohio 44135

Abstract


Ceramic thermal and environmental barrier coatings (T/EBCs) will play a crucial role in advanced gas turbine engine systems because of their ability to significantly increase engine operating temperatures and reduce cooling requirements, thus help achieve engine low emission and high efficiency goals. Under the NASA Ultra-Efficient Engine Technology (UEET) program, advanced T/EBCs are being developed for the low emission SiC/SiC ceramic matrix composite (CMC) combustor applications by extending the CMC liner and vane temperature capability to 1650 °C (3000 °F) in oxidizing and water vapor containing combustion environments. Advanced low conductivity thermal barrier coatings (TBCs) are also being developed for metallic turbine airfoil and combustor applications, providing the component temperature capability up to 1650 °C (3000 °F). The advanced T/EBC system is required to have increased phase stability, low lattice and radiation thermal conductivity, and improved sintering, erosion and thermal stress resistance, and water vapor stability under the engine high-heat-flux and thermal cycling conditions. Advanced high heat-flux testing approaches have been established for the coating developments. The simulated combustion water-vapor environment is also being incorporated into the heat-flux test capabilities for evaluating T/EBC performance at very high temperatures under thermal cycling conditions.

In this paper, ceramic coating development considerations and requirements for both the ceramic and metallic components will be described for engine high temperature and high-heat-flux applications. The performance and durability of several ZrO₂ or HfO₂/mullite and mullite/BSAS model coating systems were investigated. The underlying coating failure mechanisms and life prediction approaches will be discussed based on the simulated engine tests and fracture mechanics modeling results. Further coating performance and life improvements will be expected by utilizing advanced coating architecture design, composition optimization, in conjunction with more sophisticated modeling and design tools.



Thermal and Environmental Barrier Coatings for Advanced Turbine Engine Applications


Dongming Zhu and Robert A. Miller



Durability and Protective Coatings Branch, Materials Division
NASA John H. Glenn Research Center
Cleveland, Ohio 44135, USA

This work was supported by NASA Ultra-Efficient Engine Technology (UEET) Program


**2004 MRS Fall Meeting
Boston, MA
November 30, 2004**



Motivation


- Advanced thermal and environmental barrier coatings (T/EBCs) can significantly increase gas temperatures, reduce cooling requirements, and improve engine fuel efficiency and reliability

Combustor Vane Turbine blade




(a) Current T/EBCs

(b) Advanced T/EBCs



Revolutionary Ceramic Coatings Greatly Impact Gas Turbine Engine Technology

- Ceramic coatings are critical to future engine efficiency, power density and compactness goals




Coating Development Issues

- Low thermal conductivity
- High temperature stability
- Erosion and radiation resistance

NASA UEET Goals

- 70% NO_x reduction
- 8-15% increase in efficiency
- 8-15% reduction in CO₂






OBJECTIVES


- **High-heat-flux and simulated engine test capabilities for advanced barrier coating developments**
 - In-situ conductivity measurements and coating degradation evaluation
 - Simulated engine testing
 - Sintering, strength and fracture behavior
- **Low conductivity thermal barrier coatings**
- **The 3000 °F (1650 °C) thermal and environmental barrier coatings for SiC/SiC CMC and metallic combustors/vanes**
- **Advanced Si₃N₄ coating systems**



NASA Steady-State Laser Heat-Flux Approach for Ceramic Coating Thermal Conductivity Measurements

- A uniform laser (wavelength $10.6\ \mu\text{m}$) power distribution achieved using integrating lens combined with lens/specimen rotation
- The ceramic surface and substrate temperatures measured by 8 micron and two-color pyrometers and/or by an embedded miniature thermocouple
- Thermal conductivity measured at 5 second intervals in real time








Laser Heat Flux Testing in Water Vapor Environments for Si-Based Ceramics/Coatings

– Laser heat flux steam rig


- Precise control of heat flux and temperatures of test specimen
- Automated control of chamber temperature and steam environments
- High temperature and high heat flux testing capabilities
- Innovative “micro-steam environment” concept allows high vapor pressure, velocity and temperature as required
- Real time specimen health monitoring capability





High Pressure Burner Rig (HPBR) for Ceramic Coatings Testing


- Realistic combustion environments for specimen and component testing



- Burns jet fuel and air
- T_{gas} : up to 1650 °C (3000 °F)
- 4-12 atmospheres
- 10-30 m/s (6" ID)
- TC and optical temp. measurement
- Variable geometry




1" button TEBC coating specimen holder for the burner rig testing





Thermal Conductivity of Current Thermal Barrier Coating Systems

Current thermal barrier coatings consist of $\text{ZrO}_2\text{-8wt\%Y}_2\text{O}_3$


- relatively low intrinsic thermal conductivity $\sim 2.5 \text{ W/m-K}$
- high thermal expansion to better match superalloy substrates
- good high temperature stability and mechanical properties
- Additional conductivity reduction is achieved by incorporating micro-porosity



(a) Plasma-sprayed coating




(b) EB-PVD coating



Coating Thermal Conductivity Reductions by Porosity are limited in Practical Applications


- The conductivity reduction achieved by microcracks and micro-porosity can not persist under high temperatures due to coating sintering
- The coating mechanical properties also affected by too high porosity






ZrO₂-8wt%Y₂O₃/Mullite+BSAS/Si System under High Temperature Steady-State Laser Heat-Flux Testing


- ZrO₂-8wt%Y₂O₃/mullite+BSAS TEBC system on SiC/SiC CMC tested at $T_{\text{surface}} = 1482^\circ\text{C}$ (2700 °F) and $T_{\text{interface}} = 1300^\circ\text{C}$ (2350 °F)
- Conductivity initially increased due to sintering
- Conductivity later decreased due to delamination resulting from the large sintering shrinkage
- Coating delaminates at temperature due to sintering/creep






Sintering Behavior of the Plasma-Sprayed $\text{ZrO}_2\text{-8wt\%Y}_2\text{O}_3$ Coatings

- Sintering shrinkage as a function of time and temperature determined using dilatometer
- Sintering can induce surface cracking and delamination







Thermal Conductivity Increase Kinetics of Plasma-Sprayed $\text{ZrO}_2\text{-8wt\%Y}_2\text{O}_3$ Coatings due to Sintering

- The conductivity reduction by microcracks and micro-porosity can not persist under high temperatures due to coating sintering
- The coating durability can be affected by sintering


Thermal conductivity $\text{ZrO}_2\text{-8wt\%Y}_2\text{O}_3$ as a function of time and temperature at up to 1320 °C






Flexure Strength and Toughness Increases Kinetics as a Function of Annealing/Sintering Time

- Initially fast sintering induced strength and fracture toughness increases also observed for plasma-sprayed $\text{ZrO}_2\text{-8wt\%Y}_2\text{O}_3$ coatings





Development of Advanced Defect Cluster Low Conductivity Thermal Barrier Coatings


- Multi-component oxide defect clustering approach used for the advanced coating development – *US Patent No. 6,812,176*

e.g., $\text{ZrO}_2\text{-Y}_2\text{O}_3\text{-Nd}_2\text{O}_3(\text{Gd}_2\text{O}_3, \text{Sm}_2\text{O}_3)\text{-Yb}_2\text{O}_3(\text{Sc}_2\text{O}_3)$ systems


↪ Primary stabilizer ↪

Oxide cluster dopants with distinctive ionic sizes


- Defect clusters associated with the dopant segregation identified from moiré fringe patterns and electron energy loss spectroscopy (EELS) under high resolution TEM
- The 5 to 100 nm size defect clusters designed for the significantly reduced thermal conductivity and improved stability



Plasma-sprayed $\text{ZrO}_2\text{-13.5mol\%(Y, Nd, Yb)}_2\text{O}_3$



EB-PVD $\text{ZrO}_2\text{-12mol\%(Y, Nd, Yb)}_2\text{O}_3$




EELS elemental maps of EB-PVD $\text{ZrO}_2\text{-14mol\%(Y, Gd, Yb)}_2\text{O}_3$




Low Conductivity Oxide Defect Cluster Coatings Demonstrated Improved High Temperature Stability

- Thermal conductivity rate-of-increase significantly reduced at high temperatures for the low conductivity defect cluster thermal barrier coatings
- Phase stability also improved





Plasma-sprayed coatings



Low Conductivity Oxide Defect Cluster Coatings Demonstrated Improved High Temperature Stability


- Thermal conductivity rate-of-increase significantly reduced at high temperatures for the low conductivity defect cluster thermal barrier coatings
- Phase stability also improved






Thermal Conductivity of Oxides Cluster Thermal Barrier Coatings Tested at Higher Temperatures


- Both cubic phase low k coatings and t' tetragonal plasma-sprayed coatings showed significantly lower thermal conductivity as compared to baseline $\text{ZrO}_2\text{-8wt\%Y}_2\text{O}_3$ under higher temperatures





Furnace Cyclic Behavior of Plasma-Sprayed ZrO_2 - (Y,Gd,Yb) $_2\text{O}_3$ Thermal Barrier Coatings


- The cubic-phase ZrO_2 -based low conductivity TBC durability can be further significantly improved by an 8YSZ or low k tetragonal t'-phase interlayer
- The tetragonal t'-phase low conductivity TBCs achieved at least the baseline 8YSZ life









Effects of Defect Cluster Dopant Ratio and Bond Coat Optimization on Coating Conductivity and Furnace Cyclic Life


- Optimized dopant ratio lowered coating conductivity and improved furnace cyclic life
- Bond coat and interface processing optimization can also improve durability







Low Diffusion and High Toughness Coatings Showed Better Cyclic Life





Advanced Low Conductivity TBC Showed Excellent Long-Term High Temperature Cyclic Durability


- The low conductivity combustor and turbine airfoil thermal barrier coatings successfully tested under laboratory simulated engine thermal gradient cyclic conditions






Development of Advanced Erosion Resistant Thermal Barrier Coatings


- Advanced high toughness, multi-component erosion resistant low conductivity thermal barrier coatings also under development



(a) Burner rig erosion and impact test results at 2200 °F




(b) Room temperature erosion testing results for 2400 °F thermal gradient tested specimens



Advanced 3000 °F (1649 °C) Coatings

- High temperature stability
- Low thermal conductivity
- Excellent thermal stress resistance
- Enhanced radiative flux resistance and radiation cooling
- Improved environmental protection
- Designed functional capability



High temperature capability
thermal and radiation barrier

Energy dissipation and chemical
barrier interlayer

Secondary radiation barrier, thermal
control with chemical barrier interlayer




Environmental barrier


Ceramic matrix composite (CMC)



Advanced 3000 °F (1649 °C) Coatings Development for SiC/SiC Combustor Liner and Vane Applications


- The multicomponent hafnia(zirconia) coating/modified mullite systems demonstrated excellent cyclic durability and radiation resistance at 1650 °C (3000 °F)
- Advanced high temperature ceramic bond coats also developed






Advanced Environmental Barrier Coatings for Si_3N_4 Applications


- **Multi-layered, rare earth and silicon doped HfO_2 /mullite 2700 °F environmental barrier coating systems developed:**
 - Advanced low expansion doped HfO_2 used for high stability top layer
 - Modified mullite as the interlayer and environmental barrier
 - Doped HfO_2 or mullite 2700 °F+ capable bond coats (eliminating Si bond coat)
- **High Temperature plasma-spray technique used for coating processing**




Multi-layer coating systems for 2700 °F Si_3N_4 components



Plasma-spray processing of Environmental barrier coating







A 2700 °F capable coating system for Si_3N_4



Coating Radiation Performance Evaluation and Radiation Barrier Coatings Development



- Radiation conductivity evaluated using the laser heat flux approach
- Significant conductivity increase due to increased radiation at high temperatures especially under thermal gradients






Evaluation of Radiation Thermal Conductivity of T/EBC Systems at High Temperatures

- Radiation conductivity increases with thermal gradient and thus heat flux
- Advanced HfO_2 coatings demonstrated improved radiation resistance compared to the baseline ZrO_2 -8wt% Y_2O_3 coating





Summary and Conclusions

- **Advanced testing approaches established for ceramic coating development**
- **Real-time monitoring of coating thermal conductivity demonstrated as an effective technique to assess coating performance under simulated engine heat flux conditions**
- **The multi-component TBCs demonstrated lower conductivity, improved high temperature stability and cyclic durability required for advanced turbine airfoil and combustor applications**
- **High toughness erosion resistant turbine airfoil TBC development showed significant progress**
- **Advanced 1650 °C (3000 °F) T/EBC systems developed for Si-based ceramics**

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE March 2005		3. REPORT TYPE AND DATES COVERED Technical Memorandum
4. TITLE AND SUBTITLE Thermal and Environmental Barrier Coatings for Advanced Turbine Engine Applications			5. FUNDING NUMBERS WBS-22-714-20-09	
6. AUTHOR(S) Dongming Zhu and Robert A. Miller				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration John H. Glenn Research Center at Lewis Field Cleveland, Ohio 44135-3191			8. PERFORMING ORGANIZATION REPORT NUMBER E-14972	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration Washington, DC 20546-0001			10. SPONSORING/MONITORING AGENCY REPORT NUMBER NASA TM-2005-213437	
11. SUPPLEMENTARY NOTES Viewgraphs prepared for the 2004 Fall Meeting sponsored by the Materials Research Society, Boston, Massachusetts, November 29-December 03, 2004. Dongming Zhu, U.S. Army Research Laboratory, NASA Glenn Research Center; and Robert A. Miller, NASA Glenn Research Center. Responsible person, Dongming Zhu, organization code RMD, 216-433-5422.				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Unclassified - Unlimited Subject Categories: 23, 24, and 27 Available electronically at http://gltrs.grc.nasa.gov This publication is available from the NASA Center for AeroSpace Information, 301-621-0390.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Ceramic thermal and environmental barrier coatings (T/EBCs) will play a crucial role in advanced gas turbine engine systems because of their ability to significantly increase engine operating temperatures and reduce cooling requirements, thus help achieve engine low emission and high efficiency goals. Advanced T/EBCs are being developed for the low emission SiC/SiC ceramic matrix composite (CMC) combustor applications by extending the CMC liner and vane temperature capability to 1650 °C (3000 °F) in oxidizing and water vapor containing combustion environments. Low conductivity thermal barrier coatings (TBCs) are also being developed for metallic turbine airfoil and combustor applications, providing the component temperature capability up to 1650 °C (3000 °F). In this paper, ceramic coating development considerations and requirements for both the ceramic and metallic components will be described for engine high temperature and high-heat-flux applications. The underlying coating failure mechanisms and life prediction approaches will be discussed based on the simulated engine tests and fracture mechanics modeling results.				
14. SUBJECT TERMS Thermal barrier coatings; Environmental barrier coatings; Thermal radiation; Thermal conductivity; Defect clustering			15. NUMBER OF PAGES 35	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT	

